



شرکت فرآورده های نسوز صنعت پاسارگاد
Pasargad Industry Refractories Company (PIREFCO.)

PIREF-Mor 30

Chemical Analysis (%)

Al_2O_3	SiO_2	Fe_2O_3	TiO_2	$\text{Na}_2\text{O}+\text{K}_2\text{O}$	$\text{CaO}+\text{MgO}$
29-30	58-59	2.5-3.5	3.5-4.5	≤ 1.0	≤ 1.5

Mechanical Analysis

Refractoriness (°C)	PLC (%) at Service limit	Service limit (°C)	Grain Size (mm)	Mixing liquid, Water (%)
1625	- 2.0	1225	0-0.1	10-12