



شرکت فرآورده های نسوز صنعت پاسارگاد
Pasargad Industry Refractories Company (PIREFCO.)

PIREF-Mor 35

Chemical Analysis (%)

Al_2O_3	SiO_2	Fe_2O_3	TiO_2	$\text{Na}_2\text{O}+\text{K}_2\text{O}$	$\text{CaO}+\text{MgO}$
34-36	54-55	2.0-3.0	3.5-4.5	≤ 0.7	≤ 1.2

Mechanical Analysis

Refractoriness (°C)	PLC (%) at Service limit	Service limit (°C)	Grain Size (mm)	Mixing liquid, Water (%)
1650	- 1.8	1275	0 - 0.1	10-12